

## STATIC CO-EFFICIENT OF FRICTION

Laboratory conditions: 23°C, 50% R.H.

DISCLAIMER: All statements, information and data given herein are believed to be accurate and reliable but are presented without guaranty, warranty or responsibility of any kind, expressed or implied. Statements or suggestions concerning possible use of our products are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that all safety measures are indicated or that any measures may not be required.

Condition	Specimen	Det.	Static C oefficient of Friction
Dry	1	1	0.57
		2	0.60
		3	0.61
		4	0.68
	2	1	0.60
		2	0.67
		3	0.64
		4	0.63
	3	1	0.56
		2	0.64
		3	0.61
		4	0.62
	Sample Average		

Condition	Specimen	Det.	Static C oefficient of Friction
Wet	1	1	0.70
		2	0.67
		3	0.67
		4	0.71
	2	1	0.71
		2	0.73
		3	0.75
		4	0.72
	3	1	0.75
		2	0.72
		3	0.73
		4	0.75
	Sample Average		